



TECHNICAL DATA SHEET

CHAMÄLEON WHEEL PAINT (SILVER)

Article number:	26104
Intended use:	Car refinishing Product/ Lacquer
General characteristics:	For embellishing and repairing of steel and light metal rims and hubcaps.
Product characteristics:	<ul style="list-style-type: none">▪ Fast drying▪ Good coverage▪ Resistant to petrol, chemicals and weather influences▪ Non-fading and UV-resistant▪ Lasting gloss▪ Good surface hardness▪ Wear-resistant and scratch free▪ Excellent adhesion
Technical characteristics:	
Contents:	500 ml
Base:	Acrylic resin
VOC-content:	Approximately 90% w/w
Solid content:	Approximately 10% w/w
Coverage:	4 to 5 rims / hubcaps Approximately 1 rim / hubcap
Dust dry:	After 5 to 10 minutes
Tack free:	After 10 to 20 minutes
Hardened/re-sprayable:	After 2 hours
Heat resistant:	To 110°C

Usage:

Before use, carefully read the directions on the packaging and act accordingly.



CHAMÁLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÁLEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Pre Treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of Chamaeleon Spray Primer suitable for the surface. After drying, sand the base layer (grain 600).

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Application:

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Package: 500 ml

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via:
info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.